

AD-754 047

LUBRICATING AND COOLING FLUID FOR COLD
AND HOT ROLLING OF METALS

M. M. Gorenshtein, et al

Foreign Technology Division
Wright-Patterson Air Force Base, Ohio

11 December 1972

DISTRIBUTED BY:

NTIS

National Technical Information Service
U. S. DEPARTMENT OF COMMERCE
5285 Port Royal Road, Springfield Va. 22151

AD754047


FOREIGN TECHNOLOGY DIVISION



LUBRICATING AND COOLING FLUID FOR COLD AND HOT
ROLLING OF METALS

by

M. M. Gorenshteyn, S. Ye. Kondrashin, et al.



Approved for public release;
distribution unlimited.

Reproduced by
**NATIONAL TECHNICAL
INFORMATION SERVICE**

U S Department of Commerce
Springfield VA 22151

Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Foreign Technology Division Air Force Systems Command U. S. Air Force		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
		2b. GROUP	
3. REPORT TITLE LUBRICATING AND COOLING FLUID FOR COLD AND HOT ROLLING OF METALS			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Translation			
5. AUTHOR(S) (First name, middle initial, last name) Gorenshteyn, M.M.; Kondrashin, S.Ye.			
6. REPORT DATE 12 July 1969		7a. TOTAL NO. OF PAGES 3	7b. NO. OF REFS
8a. CONTRACT OR GRANT NO. b. PROJECT NO. 7343 c. d.		8a. ORIGINATOR'S REPORT NUMBER(S) FTD-HT-23-1545-72	
		8b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. DISTRIBUTION STATEMENT Approved for public release; distribution unlimited.			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Foreign Technology Division Wright-Patterson AFB, Ohio	
13. ABSTRACT A lubricating and cooling fluid for the cold and hot rolling of metals contained hydroxylated monoethanolamides of synthetic aliphatic acids 0.5-0.7 wt. %, a corrosion inhibitor 0.5-0.7 wt. %, and deionized water the rest. AA2016837			

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Hot Rolling Cold Rolling Heat Transfer Fluid Metalworking Lubricant Patent Amide Corrosion Inhibitor						

UNCLASSIFIED

Security Classification

EDITED TRANSLATION

FTD-HT-23-1545-72

LUBRICATING AND COOLING FLUID FOR COLD AND HOT
ROLLING OF METALS

By: M. M. Gorenshteyn, S. Ye. Kondrashin, et al.

English pages: 3

Source: USSR Patent No. 293041 (Appl. No.
1348364/23-4, July 12, 1969), 1971,
2 pages.

Requester: ASD

Translated by: Dean F. W. Koolbeck

Approved for public release;
distribution unlimited.

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION DIVISION
FOREIGN TECHNOLOGY DIVISION
WP-AFB, OHIO.

LUBRICATING AND COOLING FLUID FOR COLD AND HOT ROLLING OF METALS

M. M. Gorenshteyn, S. Ye. Kondrashin,
A. I. Vovk, L. A. Komarova,
I. A. Chamin, A. A. Petrovskiy,
and Ya. S. Shvartsbart

The invention relates to the field of cold and hot rolling of metallic strip and may be mainly applied in rolling of hard-to-work precision alloys, auto sheet, and sheet iron, which are faced with elevated requirements in terms of surface quality.

Existing lubricating and cooling fluids (LCF) for cold and hot rolling of metals are based on water and salts of amines and fatty acids.

In order to increase LCF effectiveness it is proposed that the following be added to its composition: oxyethylated monoethanol amides of synthetic fatty acids, esters of high-molecular synthetic fatty alcohols, and a corrosion inhibitor.

Composition of the LCF, wt. %: sintamid-5, 0.5-0.7; EHMSFA, 0.5-0.7; corrosion inhibitor, 0.5-0.7; remainder, deionized water.

Sintamid-5 is made up of oxyethylated monoethanol amides of synthetic fatty acids of the fraction $C_{10}-C_{16}$.

The EHMSFA are esters (waxes) of high-molecular synthetic fatty alcohols in which the number of carbon atoms is greater than C_{17} . They should satisfy the following requirements: acid number 16.1 mg KOH/g, saponification number 99.7 mg KOH, ester number 83.6 mg KOH/g, and drop temperature 56°C .

The proposed three-component aqueous emulsion (SEV) is made as follows.

A 10% concentrate is prepared in a separate vessel. All components are simultaneously introduced into a tank with the appropriate amount of water and are melted by steam, with simultaneous agitation.

The concentrate temperature should fall within the limits $70-80^{\circ}\text{C}$.

The 10% concentrate of the emulsion is introduced into the main vessel, containing water heated to $40-50^{\circ}\text{C}$, until the required working concentration is obtained.

As the lubricating and cooling fluid is used water and emulsion concentrate are added.

When the proposed aqueous emulsion SEV is used the emulsion retains its effectiveness when the strip to be rolled is heated to 500°C ; this makes it possible to carry out hot rolling of steel and imposes virtually no limitation on the rate of cold rolling.

At the temperature at which the steel is annealed, the emulsion components are decomposed into volatiles and do not leave any traces of "tarnish" on the surface of the strip.

When the SEV emulsion is used the energy and power parameters of rolling are reduced by 25-30%, making it possible to increase

reduction and to lower the number of passes and the number of intermediate annealings.

The film of SEV emulsion retained on the surface of the strip after annealing will protect the metal from corrosion.

The SEV emulsion has no objectionable odor; it is not toxic and is absolutely safe with respect to fire, as well as remaining stable during prolonged use. The service life of the emulsion is up to two weeks when water and emulsion concentrate are added as the lubricating and cooling fluid is consumed.

After use the emulsion is easily decomposed chemically; this makes it possible to pour the water remaining after treatment with chemical agents into storage vessels without danger of contaminating them.

Object of the Invention

1. The lubricating and cooling fluid for cold and hot rolling of metals, based on deionized water, *is distinguished* by the fact that in order to increase fluid effectiveness oxyethylated monoethanol amides of synthetic fatty acids, esters of high-molecular synthetic fatty alcohols, and a corrosion inhibitor are added to its composition.

2. The lubricating and cooling fluid in p. 1 *is distinguished* by the fact that the following are introduced into it (in wt. %): oxyethylated monoethanol amides of synthetic fatty acids, 0.5-0.7; corrosion inhibitor, 0.5-0.7; deionized water, to 100.